

# LEVISO LIGHT

- Subtly textured dimout fabric with a soft finished form
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 60°
- Proven acoustic properties

## APPLICATIONS



## FABRIC PROPERTIES

	Dimout
	Polyester
	300 g/m <sup>2</sup>
	0.62 mm
	290 cm
	295 cm

## FEATURES / TECHNICAL PROPERTIES

	4-5
	Alpha-w = 0.80
	Flame retardant
	Fabric must be turned
	Fabric must be turned
	Oeko-Tex
	Special colours from 400 m

## WASHING INSTRUCTIONS



## FIRE PROTECTION

Class 1 (EN 13773)  
M1 (NF P 92-503/5/7)  
Type B (BS 5867-2)



**Leviso Light**
**OPTICAL AND SOLAR COEFFICIENTS ( $\pm 5\%$ , DIN EN 410)**

Colour	$T_V$	$T_S$	$R_S$	$A_S$	$F_C$	$g_{tot}$
1	0.6	1.0	59.8	39.2	0.54	0.39
2	0.6	1.0	59.8	39.2	0.54	0.39
3	0.6	1.0	59.8	39.2	0.54	0.39
8	0.6	1.0	59.8	39.2	0.54	0.39
9	0.0	0.8	44.5	54.7	0.64	0.46
11	0.0	0.8	44.5	54.7	0.64	0.46
12	0.0	0.8	44.5	54.7	0.64	0.46
14	0.0	0.9	37.1	62.0	0.68	0.49
17	0.0	0.8	44.5	54.7	0.64	0.46
18	0.0	0.9	37.1	62.0	0.68	0.49
19	0.0	0.9	37.1	62.0	0.68	0.49
23	0.0	0.9	37.1	62.0	0.68	0.49
25	0.0	0.9	37.1	62.0	0.68	0.49
27	0.6	1.0	59.8	39.2	0.54	0.39
28	0.0	0.9	37.1	62.0	0.68	0.49
29	0.0	0.9	34.0	65.1	0.70	0.51
30	0.0	0.9	34.0	65.1	0.70	0.51
31	0.0	0.9	37.1	62.0	0.68	0.49
32	0.0	0.8	44.5	54.7	0.64	0.46
33	0.6	1.0	59.8	39.2	0.54	0.39

$T_V$  Visible light transmission

$R_S$  Solar reflectance

$F_C$  Shading factor

$T_S$  Solar transmission

$A_S$  Solar absorption

$g_{tot}$  Total g-value


$F_C + g_{tot}$ : Value calculated with glass:  $0.72 / U_g = 1.6 \text{ W/m}^2 \text{ K}$ , DIN EN 13363-1

**Leviso Light**


1



2



3




8



9




11



12




14



17



18



19



23



25



27




28




29



30



31



32



33

Colours shown are not binding