



## OSCURANTE

- Smooth dimout fabric with a pleasing haptic and colour matched reverse for a uniform appearance inside and out
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 72°
- Proven acoustic properties

### APPLICATIONS



### FABRIC PROPERTIES

	Dimout
	Polyester
	250 g/m <sup>2</sup>
	0.45 mm
	295 cm
	300 cm

### FEATURES / TECHNICAL PROPERTIES

	5-6
	Alpha-w = 0.60
	Flame retardant
	Applicable in humid areas
	Suitable for Wave
	Oeko-Tex
	Special colours from 200 m

### WASHING INSTRUCTIONS



### FIRE PROTECTION

Class 1 (EN 13773)  
Class 1 (UNI 8456)  
Type B (BS 5867-2)



**Oscurante**
**OPTICAL AND SOLAR COEFFICIENTS ( $\pm 5\%$ , DIN EN 410)**

Colour	$T_V$	$T_S$	$R_S$	$A_S$	$F_C$	$g_{tot}$
<b>328</b>	0.2	0.3	56.8	42.9	0.56	0.40
<b>331</b>	0.0	0.2	45.4	54.4	0.63	0.45
<b>334</b>	0.1	0.2	54.1	45.7	0.57	0.41
<b>337</b>	0.0	0.3	31.5	68.2	0.72	0.52
<b>338</b>	0.0	0.2	28.1	71.7	0.74	0.53
<b>339</b>	0.0	0.2	33.1	66.7	0.71	0.51
<b>340</b>	0.0	0.2	40.5	59.3	0.61	0.48
<b>343</b>	0.0	0.2	32.3	67.5	0.71	0.51
<b>344</b>	0.0	0.2	31.6	68.2	0.72	0.52
<b>752</b>	0.0	0.2	41.9	57.9	0.65	0.47
<b>756</b>	0.0	0.2	47.7	52.1	0.62	0.44
<b>757</b>	0.0	0.2	37.4	62.4	0.68	0.49

$T_V$  Visible light transmission

$R_S$  Solar reflectance

$F_C$  Shading factor

$T_S$  Solar transmission

$A_S$  Solar absorption

$g_{tot}$  Total g-value

$F_C + g_{tot}$ : Value calculated with glass:  $0.72 / U_g = 1.6 \text{ W/m}^2 \text{ K}$ , DIN EN 13363-1

**Oscurante**

328



331



334



337



338




339



340



343



344



752



756



757

Colours shown are not binding